

NORSOK – Coating system no. 7

(shall be pre-qualified)



Carbon steel

- Submerged
- Splash zone

System No.	Surface preparation	Coating system	DFT μm	Test report number
Carbon steel, submerged				
7-25	Sa 2½	Baltoflake Baltoflake	700 <u>700</u> 1400	3410-10-0014 Mt03 Norsok M-501, Rev.5
7-26	Sa 2½	Baltoflake Ecolife Baltoflake Ecolife	700 <u>700</u> 1400	3410-10-0014 Mt04 Norsok M-501, Rev.5
7-22	Sa 2½	Jotacote Universal, alum. Jotacote Universal	200 <u>150</u> 350	3410-06-0029 Mt08, Rev.A Norsok M-501, Rev.5
7-24	Sa 2½	Jotamastic 87 Aluminium Jotamastic 87	200 <u>150</u> 350	3410-07-0001 Mt07 Norsok M-501, Rev.5
7-27	Sa 2½	Jotamastic 87 GF Jotamastic 87 GF	250 <u>250</u> 500	Report: SL 11589
7-29	Sa 2½	Jotamastic SF, alum. Jotamastic SF	150 <u>200</u> 350	3410-10-0049 Mt07
7-28	Sa 2½	Marathon Marathon	250 <u>250</u> 500	Report: SL 11587
7-14	Sa 2½	Marathon IQ GF Marathon IQ GF	300 <u>300</u> 600	78.1021.13 Norsok M-501, Rev.3
Carbon steel, splash zone				
7-9	Sa 2½	Baltoflake Baltoflake	750 <u>750</u> 1500	78.1021.10 Norsok M-501, Rev.3
7-22	Sa 2½	Jotacote Universal, alum. Jotacote Universal	200 <u>150</u> 350	3410-06-0029 Mt08, Rev.A Norsok M-501, Rev.5
7-25	Sa 2½	Baltoflake Baltoflake	700 <u>700</u> 1400	3410-10-0014 Mt03 Norsok M-501, Rev.5
7-26	Sa 2½	Baltoflake Ecolife Baltoflake Ecolife	700 <u>700</u> 1400	3410-10-0014 Mt04 Norsok M-501, Rev.5
7-27	Sa 2½	Jotamastic 87 GF Jotamastic 87 GF	250 <u>250</u> 500	Report: SL 11589
1S-9	Sa 2½	Jotamastic 87 GF Jotamastic 87 GF Hardtop XP	250 250 <u>50</u> 550	Report: SL 11590

NORSOK – Coating system no. 7

(shall be pre-qualified)



- Carbon steel
- Submerged
 - Splash zone

System No.	Surface preparation	Coating system	DFT μm	Test report number
7-28	Sa 2½	Marathon Marathon	250 <u>250</u> 500	Report: SL 11587
1S-10	Sa 2½	Marathon Marathon Hardtop Optima	250 250 <u>60</u> 560	Report: SL 11588