

# NORSOK – Coating system no. 8



Structural carbon steel with operating temperature  $\leq 80^{\circ}\text{C}$  in internal and fully dry and ventilated areas

System no.	Surface preparation	Coating system	DFT $\mu\text{m}$
8-1	Sa 2½	Jotamastic 87	<u>150</u> <b>150</b>
8-2	Sa 2½	Barrier Penguard Tie Coat 100	60 <u>25</u> <b>85</b>
8-3	Sa 2½	Jotacote Universal	<u>150</u> <b>150</b>
8-4	Sa 2½	Primastic Universal	<u>150</u> <b>150</b>