

NORSOK – Coating system no. 5

(passive fire protection material shall be pre-qualified)



Under fire protection

System No.	Surface preparation	Coating system	DFT μm
5A Under epoxy based fire protection			
5A-1	Sa 2½	Penguard Primer Epoxy based fire protection *)Jotaproof Topcoat	50 as required 75
5A-2	Sa 2½	Penguard Primer Epoxy based fire protection *)Hardtop AS	50 as required 50
5A-3	Sa 2½	Barrier Penguard Tie Coat 100 Epoxy based fire protection *)Jotaproof Topcoat	60 25 as required 75
5A-4	Sa 2½	Barrier Penguard Tie Coat 100 Epoxy based fire protection *)Hardtop AS	60 25 as required 50
*) It is recommended to add a coat of high quality epoxy paint under the topcoat			
5B Under cement based fire protection			
5B-5	Sa 2½	Barrier Jotacote Universal Cement based fire protection Jotaproof Topcoat	60 200 as required 75
5B-6	Sa 2½	Barrier Jotamastic 87 Cement based fire protection Hardtop AS	60 200 as required 50